

Amendments to the Specification:

Please insert the following paragraph on page 9, line 7, to be the first paragraph following Table 1:

A preferred adhesive of the invention contains at least 30 wt% of a hydrogenated synthetic resin, about 0.1 to 20 wt% of a hydrocarbon oil and about 1 to 25 wt% of a wax. In order to improve the cohesive strength of the pick-up adhesive, the material can contain about 0.1 to about 7 wt% of a polymer such as ABA block copolymer, an ethylene vinyl acetate polymer, or other typical adhesive polymers. A second preferred hot melt pick-up adhesive can comprise at least 70 to 85 wt% of a hydrogenated synthetic resin, about 5 to 12 wt% of a hydrocarbon oil and about 6 to 15 wt% of a wax.